



<b>SCH-40</b> PRESSURE PIPE PVC1120 ASTM D1785  	SIZE	O.D.	MIN. WALL	WEIGHT PER 100'	SOCKET DEPTH INCHES	FEET PER PALLET	PALLETS PER T.L.	BELLED PART NO.
	1/2"	.840	.109	16.18	2.000	8400	44	42015
	3/4	1.050	.113	21.58	2.125	6600	40	42030
	1	1.315	.133	32.00	2.375	5400	32	42046
	1 1/4	1.660	.140	43.40	2.750	4000	32	42056
	1 1/2	1.900	.145	51.83	3.000	3600	28	42070
	2	2.375	.154	69.71	3.000	2800	24	42085
	2 1/2	2.875	.203	110.57	3.500	2240	20	42102
	3	3.500	.216	144.82	4.000	1500	20	42111
	4	4.500	.237	213.29	5.000	580	28	47675
	6	6.625	.280	375.79	6.500	400	20	47720
	8	8.625	.332	582.30	7.000	280	16	47735
	10	10.750	.365	803.40	7.500	160	16	47745
12	12.750	.406	1064.45	8.000	120	12	47756	
16	16.000	.500	1658.84	10.000	120	12	47775	

STANDARD LENGTH 20' EXCEPT 4", 6", 8", 10", 12" & 16" WHICH ARE 20' LAYING LENGTH. NOT RECOMMENDED FOR THREADING.

SCH-80 PIPE IS FURNISHED IN PLAIN END (PE) 20' LENGTHS.

<b>SCH-80</b> PRESSURE PIPE PVC1120 ASTM D1785  	1/2"	.840	.147	20.63	PE	5200	60	43010
	3/4	1.050	.154	28.02	PE	4400	48	43025
	1	1.315	.179	41.23	PE	5200	32	43045
	1 1/4	1.660	.191	57.06	PE	4000	32	43065
	1 1/2	1.900	.200	69.19	PE	2360	40	43080
	2	2.375	.218	95.89	PE	1860	32	43095
	2 1/2	2.875	.276	146.24	PE	1160	36	43115
	3	3.500	.300	195.88	PE	1500	20	43120
	4	4.500	.337	286.26	PE	580	28	43135
	6	6.625	.432	546.56	PE	400	20	43150
	8	8.625	.500	830.24	PE	280	16	43165
	10	10.750	.593	1230.78	PE	160	16	43170
	12	12.750	.687	1692.06	PE	120	12	43175

SCH-80 PIPE IS RECOMMENDED FOR THREADING.

**PRESSURE RATINGS  
FOR CRESLINE - PVC PIPES  
AT 73.4° F**

SIZE	½	¾	1	1¼	1½	2	2½	3	4	6	8	10	12	16
SCH-40	600	480	450	370	330	280	300	260	220	180	160	140	130	130
SCH-80	850	690	630	520	470	400	420	370	320	280	250	230	230	-

**CONVERSION CHART FOR PRESSURE RATINGS  
AT VARIOUS TEMPERATURES FOR CRESLINE - PVC PIPE**

TEMPERATURE °F	73.4°	80°	90°	100°	110°	120°	130°	140°
CONVERSION FACTOR	1.00	.88	.75	.62	.50	.40	.30	.22

PRESSURE RATING IS THE ESTIMATED MAXIMUM PRESSURE THAT WATER AS THE MEDIUM IN THE PIPE CAN EXERT CONTINUOUSLY WITH A HIGH DEGREE OF CERTAINTY THAT FAILURE OF THE PIPE WILL NOT OCCUR.

DO NOT USE PLASTIC PIPE AND FITTINGS FOR COMPRESSED AIR.

**PALLET QUANTITY PVC PRESSURE PIPE**

PIPE SIZE	FEET PER PALLET	WT. PER PALLET
		SCH-40
½"	8400	1360
¾"	6600	1425
1"	5400	1728
1¼"	4000	1736
1½"	3600	1866
2"	2800	1952
2½"	2240	2477
3"	1500	2173
4"	580	1238
6"	400	1504
8"	280	1631
10"	160	1286
12"	120	1278
16"	120	1991

PIPE SIZE	FEET PER PALLET	WT. PER PALLET
		SCH-80
½"	5200	1073
¾"	4400	1233
1"	5200	2144
1¼"	4000	2283
1½"	2360	1633
2"	1860	1784
2½"	1160	1697
3"	1500	2939
4"	580	1661
6"	400	2187
8"	280	2325
10"	160	1970
12"	120	2031



CRESLINE PLASTIC PIPE CO., INC.

[www.cresline.com](http://www.cresline.com)

600 Cross Pointe Blvd.  
264 Silver Spring Rd.  
2100 South 35th St.  
3801 East Hwy. 31

Evansville, IN 47715  
Mechanicsburg, PA 17050  
Council Bluffs, IA 51501  
Corsicana, TX 75109

812-428-9350  
717-766-2566  
712-322-2294  
903-872-8475

Fax 812-428-9353  
Fax 717-697-2371  
Fax 712-322-6673  
Fax 903-872-7732