



AUSTINVILLE LIMESTONE CO. INC.

223 Newtown Church Road Austinville Va 24312

800-289-5963

Product Analysis

Pelletized Dolomitic Limestone

Also sold as: Pelletized LawnLime and Pro Pellets

	Minimum Guaranteed
SCREEN ANALYSIS (before pelletizing)	% Passing
10 mesh	100%
20 mesh	95%
40 mesh	90%
50 mesh	85%
60 mesh	80%
100 mesh	70%
200 Mesh	60%
CHEMICAL ANALYSIS	Content by Weight
Calcium (Ca)	21.5%
Magnesium (Mg)	11.0%
Calcium Oxide (CaO)	30.0%
Magnesium Oxide (MgO)	18.0%
Calcium Carbonate (CaCO ₃)	54.0%
Magnesium Carbonate (MgCO ₃)	38.0%
Calcium Carbonate Equivalent (CCE)	99.0%
Effective Neutralizing Power (ENP)	1768 lbs. per ton
Effective Neutralizing Value (ENV)	83.0%
Total Neutralizing Power (TNP)	99.0%
Relative Neutralizing Value (RNV)	92.0%
This product requires 1814 lbs. to equal one ton of standard liming material (with CCE of 90%).	
Agricultural Liming Materials Classification	Fine Pulverized
CAS# 16389-88-1	
Moisture Content	<1%

This product is duly registered for sale with the Virginia Department of Agriculture and Consumer Services, meeting all minimum standards as set forth and prescribed by that department and the Code of Virginia.